

Product Code 941800



## One Pro Putty + Primer

# No need to apply primer after application of this putty

### PRODUCT FEATURES AND BENEFITS



#### 2-in-1 Product

A Mixture of putty & primer in one product



#### Faster Painting

Reduced primer coat leads to a faster painting job



#### Excellent Smoothness

Gives excellent smoothness after application of paint



#### Other Features

1. Excellent whiteness
2. Ease Of Application
3. Strong Adhesion
4. Chalking Resistant
5. Alkali resistant

### PRODUCT DETAILS



#### MATT FINISH

#### COVERAGE

35-40 sq.ft/Kg or

3.25-3.72 sq.m/Kg for 2 coats\*

Only on the correctly prepared surface using recommended system.



Actual coverage may change from the mentioned coverage depending on the method of application surface condition.

#### AVAILABLE PACKS



### PROCESS TO APPLY (PRE-PAINTING STEPS)

#### Plaster



New masonry surfaces must be allowed to cure completely. The recommended curing period is 28 days for new masonry surfaces ensuring they are water cured on daily basis.

#### Cleaning



Surface should be free from any loose paint, dust or grease. Growth of fungus, algae or moss should be removed by wire brushing and water.

#### Chalky Substrates



When the underlying surface exhibits chalkiness, please use water curing for some time and then apply a layer of Birla Opus One Pro Smooth Primer before topcoat application.

#### Cracks



Fill surface cracks of up to 5 mm width & 3 mm depth using Birla Opus Alldry Crack Master, applied as per instructions given in the latest PIS before further steps. Loose plaster, structural cracks, etc. need to be treated as per standard construction practices.

#### Holes and Dents



In case of dents and holes use cement putty or a mix of white cement and fine sand in the ratio 1:3.



### Primer Application

For both freshly plastered or repainting surface, apply one coat of Birla Opus Pro Smooth primer by thinning 1 litre of primer with 600 ml of water and allow it to dry for minimum 4 hrs.



### Putty+Primer Application

Smoothen the surface by filling dents and undulations with thin coat of Birl Opus One Pro Putty+Primer. Allow it to dry for 4 – 6hrs. Apply second coat of putty if required. Sand with sandpaper and wipe it.



### Topcoat Application

Apply Birla Opus One Topcoat. A gap of 4 to 6 hrs to be given after each coat for drying.

## PROCESS TO APPLY (POST-PAINTING CARE)



- Ensure dry dust cleaning at regular intervals.
- While cleaning, wipe gently without intense pressure.
- Give 2 weeks of drying time post application of paint, before wet cleaning the wall.

## TECHNICAL INFORMATION

**Shelf Life:** 36 months from date of manufacture

**Drying Time:** Surface dry time 30 minutes\*

**Recoating Time:** 4-6 hours\*

**Flash point IS101/1987 Part 1, Sec 6: Not Applicable.**

## SAFETY ASPECTS

- Do not apply when ambient temperature might drop to a level below 10°C within 4 hours of application Do not apply if relative humidity is higher than 90%.
- Store the container with the lid tightly closed in an upright position, in a cool, dry place.
- Keep out of reach of children and away from eatables.
- May be harmful if swallowed. In case of ingestion, seek immediate medical attention.
- Wear eye protection during application. In case of contact with eyes, rinse immediately with plenty of water and seek medical advice.
- In case of skin contact immediately wash skin with soap and plenty

- of water. Get medical attention if irritation develops or persists.
- Do not breathe vapor or spray. It is recommended to wear suitable nose pad during sanding and surface preparation to avoid dust inhalation.
- Do not pour leftover paint down the drain or in water courses.
- In the event of spills, contain spillage using sand or mud.
- Lead content does not exceed more than 90 parts per million.
- Kindly refer to the MSDS, which gives detailed information on safety measures while handling the paint, which is available on request.