



STYLE SUPER BRIGHT ACRYLIC DISTEMPER

The best things in life begin with a clean slate. That's why, with Style Super Bright Distemper, you get superior[#] brightness, opacity, and a smooth finish at economical prices to start afresh with your dream home.

PRODUCT FEATURES[#]



SUPERIOR BRIGHTNESS

Enhanced brightness to ensure an exceptional finish and richness



IMPROVED OPACITY

Improved hiding to ensure increased coverage



EASE OF APPLICATION

Smooth and hassle-free application with brush and roller



WATER RESISTANCE

Designed to offer better resistance to water

PRODUCT DETAILS



MATT FINISH

3 BASES AVAILABLE

White, Pastel and Mid-Tone

COVERAGE

6.5-8.36 sq.m/kg[#]
(70-90 sq.ft/kg[#]) for 2 coats
(On Primer + Acrylic Putty + Primer)



1500+
SHADES AVAILABLE*



PACK SIZES



PROCESS TO APPLY

PRE PAINTING STEPS



1. Plaster

New masonry surfaces require complete curing. It's recommended to water-cure daily for 28 days



2. Cleaning

Clean surface thoroughly, removing loose paint, dust, or grease. Remove fungus, algae, or moss with wire brushing and water. Areas affected by growth require specific biowash treatment



3. Filling of Cracks

To fill cracks up to 3mm, use Birla Opus Alldry Crack Master. For larger cracks, use a 1:4 ratio of cement to river sand for plastering. For extensive cracks, consult a structural engineer for repair before painting



4. Filling of Holes and Dents

To repair dents and holes, choose between cement putty or a combination of white cement and fine sand, mixed at a 1:3 ratio



5. Special Instructions for Interior

Before applying to interior surfaces with continuous seepage or dampness, address and rectify the source of leakage

PAINTING STEPS

- Apply one coat of Birla Opus Primer (WT/ST)
- Allow it to dry for 4-6 hrs for WT & 6- 8 hrs for ST
- Apply one/two coats of Birla Opus Acrylic Putty to fill dents, minor cracks, smoothen and level the surface depends on condition of the substrate
- Allow it to dry for 4-6 hrs
- Sand with emery paper No. 180/320, then wipe away any loose powder
- Apply one coat of Birla Opus Primer (WT/ST)
- Allow it to dry for 4-6 hrs in case of WT and 6-8 hrs for ST
- Sand with emery paper No. 320, then wipe away any loose powder
- Gradually mix 1 kg of Birla Opus Style Super Bright Distemper with 600-650ml of clean water
- Apply 2-3 coats using a brush and roller, allowing 4-6 hrs between each coat

PRECAUTIONS

- Refrain from applying the product when the temperature is anticipated to fall below 10°C or within 4 hours of application. Do not apply if relative humidity >90%
- Ensure the brush is not excessively thinned or extended during application
- Utilize Birla Opus machine colorants exclusively for tinting purposes
- Thoroughly stir and strain the product before application
- Tinted paints necessitate vigorous shaking after both the addition of tint and before use
- Store the product in well-ventilated areas with the lid securely closed, away from potential ignition sources and flames
- Keep the product out of reach of children and away from eatables
- In case of skin contact or eye contact, rinse thoroughly with plenty of water and seek medical advise immediately. May be harmful if swallowed. In case of ingestion, seek immediate medical attention
- Do not breathe vapor or spray, wear a suitable nose pad during sanding and surface preparation to avoid dust inhalation

TECHNICAL INFORMATION



DRYING TIME

Surface dry time 30-45 mins
(Varies on climatic conditions)



RECOATING

4-6 hrs (Varies on climatic conditions)



THINNING

60 - 65%



FLASH POINT

Not applicable. This is a water based product and is non-flammable



STABILITY OF THINNED PAINT

Strictly use within 24 hrs



SHELF LIFE

36 months

POST APPLICATION INSTRUCTIONS

- Paint films typically take 2 weeks to develop adequate strength
- Maintaining a clean and well-kept living space contributes to the longevity of the finish

#TERMS & CONDITIONS

Superior Brightness:

Against majority of the players in the same product category, basis internal lab tests and field validation reports

Improved Opacity:

Against majority of the players in the same product category, basis internal lab tests and field validation reports

Ease of application:

Against majority of the players in the same product category, basis field validation reports

Water resistance:

Against majority of the players in the same product category, basis internal lab tests

Coverage:

Surface preparation & painting steps for each product should be followed as recommended in its Product Information Sheet (PIS)

As per internal lab tests

Actual coverage may change from the mentioned coverage depending on the method of application and surface condition

Increased colour options:

Against majority of the players in the same product category

For further details, please reach out to our team via either of the following methods:

Contact number: 1800-120-1234 Email ID: opuscare@adityabirla.com