



**936002**  
**ALLDRY WALL FIX4**  
Waterproof Coating

Alldry Wall Fix 4 is a waterproofing basecoat for vertical walls. It acts as a perfect waterproofing basecoat for all Birla Opus Exterior Emulsions. It is a unique product owing to its high water resistance and ability to withstand high water pressure.

**PRODUCT BENEFITS**



**WATERPROOFING**

Safeguards against Positive hydrostatic pressure of upto 5 Bar on wall\*



**MECHANICAL STRENGTH**

The acrylic fibres give toughness to the thick film



**ADHESION**

Strong adherence to the concrete/masonry substrate




**WARRANTY**

Up to 4-year waterproofing warranty on exterior-walls as a basecoat under Birla Opus Exterior topcoat. The Warranty period will depend on Birla Opus exterior topcoat applied.\*\*

**PRODUCT DETAILS**

**ESTIMATED FORCED COVERAGE**

3.71-4.18 sq.m/L  
(40-45 sq.ft/L)



**Recommended usage** – To be applied on plastered vertical surface like parapet, sunshades and exterior walls using brush or roller.

**AVAILABLE PACKS**



**COLOURS AVAILABLE**



**WHITE**

**DRYING TIME TO TOUCH**



between recoats

**APPLICATION DETAILS**

**SURFACE PREPARATION**

**New masonry surfaces must be allowed to cure completely for 28 days.**

Existing Surface should visually inspected for conditions, prepare the surface thoroughly by cleaning, washing, and removing dust, dirt, oil, grease, and loose particles to avoid adverse effects on the adhesion of newly applied products.

**REPAIRING**

**Areas with Structural defects need to be rectified before application.**

All should be properly treated. For filling cracks up to 5mm, use Alldry Crack Master Paste. Bigger cracks, damaged or hollow portions, sharp edges, etc. must be cut and repaired with a polymer-modified mortar using Alldry Repair Master.

**The surface should be Surface Saturated Dry (SSD) before application of coating.**



\*\*Please refer to the warranty document of relevant Birla Opus Exterior topcoat for more details.  
\*\*Based on lab tests

### ALLDRY WALL FIX 4

	STEP	% DILUTION	RECOATING PERIOD	ESTIMATED FORCED COVERAGE
<b>Vertical Surface Application</b> Fresh Painting: 2 coats application with effective coverage of 25 sq ft/L or 40-45 sq.m/L Repainting: 1 undiluted coat application with effective coverage 30-35 sq ft/L or 40-45 sq.m/L	Primer Coat	10% with potable water	4-6 hours	Effective coverage 30-35 sq ft/L or 3.71-4.18 sq.m/L
	1 <sup>st</sup> Coat	Without Dilution	4-6 hours	

### SAFETY MEASURES

- Kindly request for the MSDS, for detailed information on safety measures while handling the paint.
- The container must be stored in a cool, dry place with the lid tightly closed in an upright position.
- Keep it away from children and eatables.
- If swallowed, seek medical attention immediately.
- Always wear eye protection during application to avoid contact. Rinse immediately with plenty of water in case of accidental eye or skin contact and seek medical advice if irritation persists.
- The product is free of Lead, Mercury, Chromium, Arsenic and other heavy metal compounds.
- The left-over paint/drums must not be disposed of in soil or drains or water courses.

### PRECAUTIONS

- Apply when ambient temperature is between 10°C - 45°C.
- Clean with bleaching solution for surfaces having heavy algal infestation.
- The material must always be closed when not in use.
- Do not apply if the surface is wet or visibly damp or when humidity > 80%.
- Do not apply if rain is expected within 2 days post application.

### TECHNICAL INFORMATION

Drying Time	4-6 hours
Appearance	Viscous liquid
Color	White
Tensile Strength	Upto 2.5 N/mm <sup>2</sup>
% Elongation	Upto 100
Resistance to Positive Hydrostatic pressure	Passes 5 bar
Shelf Life	36 months